

PLEXIGLAS® Film Yellow 1F008

Product Data Sheet

Product

PLEXIGLAS® Film 1F008 is a yellow transparent weather resistant acrylic film, especially developed for laminates.

The film shows an excellent performance in longtime outdoor weathering. It provides high protection of laminating systems from degradation caused by UV radiation.

Its very smooth surface leads the film to have an excellent optical and flatness quality surface.

Application

PLEXIGLAS® Film 1F008 is recommended for traffic control signs according to different standards like DIN 6171-1 and ASTM D4956-01.

PLEXIGLAS® Film 1F008 can be laminated on different polymeric films and sheets. Laminated decoration films based on PLEXIGLAS® are suitable for a wide range of molding processes such as thermoforming, and insert molding.

Due to its good optical property and lamination behavior with pressure sensitive adhesive (PSA), PLEXIGLAS® Film 1F008 can be used as overlay laminates for reflective products for traffic control and guidance signs.

Processing

PLEXIGLAS® Film 1F008 can be laminated onto polymeric substrates such as films or extruded sheets based on PVC, PC, ABS, PMMA and ASA by in-line or roll-to-roll heat lamination.

The film can be cut-to-size or die cut.

PLEXIGLAS® Film 1F008 has a good printability behavior in all printing technologies such as gravure, flexography and digital. In most of the cases any pre-treatment or primers are not required.

High quality laminates in between PLEXIGLAS® Film 1F008 and other polymeric substrates such as PET, PC, PP, PE and PVC can be achieved with pressure sensitive adhesives (PSA) or solvent based adhesives.

Sales range

PLEXIGLAS® Film 1F008 is delivered on rolls, in a thickness of 75 µm and a width of 1270 mm.

Tailor made rolls can be produced under prior commercial agreement.

Technical data

Properties	Test method	Unit	Value
Optical			
Color coordinate x	DIN 5033		0,4703
Color coordinate y	DIN 5033		0,5018
Luminous transmittance τ_{D65}	ISO 13468-2	%	71,3
UV transmittance (280 – 380 nm)	DIN EN 410:2011	%	< 0,5
Refractive Index	ISO 489	%	1,49
Mechanical			
Tensile stress at yield (σ_y)	ISO 527-3	MPa	56
Yield strain (ϵ_y)	ISO 527-3	%	6,5
Nominal strain at break (ϵ_B)	ISO 527-3	%	40
Thermal			
Glass transition temperatur T_g (DSC)	ISO 11357	° C	113
Miscellaneous			
Accelerated weathering resistance	ISO 4892-2 method A, cycle 1, 65% RH	h	5000 No visible change
Specific gravity	DIN 53479	g/cm ³	1,17
Surface tension	DIN 53364	mN/m	50

® = registered trademark PLEXIGLAS is a registered trademark of Evonik Röhm GmbH, Darmstadt, Germany.
Certified to DIN EN ISO 9001 (Quality) and DIN EN ISO 14001 (Environment)

Evonik is a worldwide manufacturer of PMMA products sold under the PLEXIGLAS® trademark on the European, Asian, African and Australian continents and under the ACRYLITE® trademark in the Americas.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Performance Materials GmbH

Acrylic Polymers

Kirschenallee, 64293 Darmstadt, Germany

films@evonik.com www.plexiglas.net www.evonik.com

Ref. No. 239-33 July 2015